

Direct to Metal Paint

A smooth, semi-gloss coating which can be applied direct to bare, previously painted or weathered metal surfaces providing a hardwearing finish. It offers excellent anti-corrosive properties whilst maintaining excellent adhesion attributes. For added protection, use in conjunction with Leyland Anti-Corrosive Metal Primer.

Recommended uses

Interior ✓ Exterior ✓

Type of substrate

Bare, previously painted or weathered metal surfaces. For further information on substrates please contact Technical Advisory on 01924 354354.

Colour availability

Black, White, Silver & Gold (2.5ltr & 750ml)

Finish

Semi-gloss

Volume solid

50 %

Coverage

1 litre will cover approximately 10 square metres depending on the nature and porosity of the surface. Strong or contrasting colours may require additional coats. When using more than one tin of a colour in the same area, intermix before use.

Drying time

Recoat after 2 hours

Transportation and storage

STORE AWAY FROM HEAT AND FLAME.

To avoid the risk of spillage, always store and transport in a secure upright position.

Lift with care - gross weight does not exceed 4 kilograms.

VOC content

HIGH VOC CONTENT 25-50%

VOCs (Volatile Organic Compounds) contribute to atmospheric pollution.

EU limit value for this product (Cat A/i): 500g/l (2010) This product contains max 500g/l VOC.

Film thickness

Wet: 111 micron

Dry: 50 micron

Preparation

All surfaces should be sound, clean, dry and free from grease. Remove any crazed or flaking paint. Rub down sound glossy surfaces with fine waterproof abrasive paper and rinse thoroughly to provide a key. Avoid the inhalation of dust. Wear a suitable face mask if dry sanding. Special

precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain harmful lead. For further advice contact Technical Advisory on 01924 354354.

Application

Stir well before use. Apply by brush or roller. The brush should be fully loaded for best results. For optimum performance, apply a second coat approx. 2 hours after the 1st application when the film is touch dry but not fully cured. Depending on conditions, the product should be completely dry after 16-24 hours.

Cleaning

Remove as much product as possible from application equipment before cleaning. Clean equipment immediately after use in White Spirit or Turpentine Substitute. Replace lid firmly. Some local authorities have special facilities for the disposal of waste coatings. Do not empty product into drains or watercourses.

Warning

- **Flammable liquid and vapour.**
- Contains 2-butanone oxime. May produce an allergic reaction.
- Safety data sheet available on request.
- Repeated exposure may cause skin dryness or cracking.
- Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking.
- If medical advice is needed, have product container or label at hand.
- Keep out of reach of children.
- Dispose of contents/container to a waste disposal site in accordance with local/national regulations.
- Do not get in eyes, on skin, or on clothing.
- IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.
- IF ON SKIN: Wash with plenty of water. Do not use solvent thinners or White Spirit.
- IF SWALLOWED: Call a POISON CENTRE or doctor if you feel unwell.
- Ensure maximum ventilation during application and drying.
- Not recommended for interior use on large surface areas, or in confined spaces.
- Store in a well-ventilated place. Keep cool.
- Keep container tightly closed.

