

CORROLESS RF35 WHITE

TWO PACK EPOXY TANK LINING

DESCRIPTION A two-component, high build, solvent-less epoxy coating, reinforced with self-leaving glass flake.

PRODUCT FEATURES AND RECOMMENDED USES

- Glass reinforced for increased impermeability.
- Nato Stock number 0442-8010-25-150-0973
- Approved in conjunction with Corroless EPF for the interior of bulk fuel tanks including aviation fuel. (MIL-PRF-4556F and DEF STAN 80/97).
- Applications include fuel tanks, non-potable water tanks, pipe linings, cargo holds, sewage works, etc.

TECHNICAL DATA

Volume Solids (±2%) 96%.

Specific Gravity 1.3 kg/litre (mixed material).

Film Thickness **Wet Film** 208 microns. **Dry Film** 200 microns.

Theoretical Coverage 4.8 m²/litre at 200 microns dft. Practical coverage rate can vary depending on application method, temperature, profile and porosity of the substrate.

Application Airless spray, brush or roller.

Mixing Ratio 2:1 by volume (base to hardener).

Pot Life (at 18°C) 45 minutes.

Drying Times
at recommended dft

	10°C	18°C
Dust Free	12 hours	8 hours
Hard Dry	30 hours	16 hours
Overcoating Minimum	30 hours	16 hours
Maximum	3 days	3 days

Thinners and Cleaning solvent

Thinning not recommended. Solvent Gun Wash may be used for cleaning only.

Finish

Gloss.

Colour

Off White

Storage

Product has a shelf life of 2 years when stored in dry, cool conditions and protected from frost.

CORROLESS Corrosion Control, Worldwide Headquarters, Kelvin Way, WEST BROMWICH, West Midlands B70 7JZ,

Telephone:
+44 (0)121 524 2235

Fax:
+44 (0)121 553 2787

Web:
www.corroless.com

e-mail:
contact@corroless.com



CORROLESS RF35 WHITE

TWO PACK EPOXY TANK LINING

APPLICATION DETAILS

Surface Preparation All surfaces when coated should be firm, clean, dry and free from all oil, grease, and other contamination. This is a finish coat and should be applied over Corroless primers or intermediate coats.
Approved primer: Corroless EPF.

Application Always follow the overcoating time for the primer.

Method	Airless Spray	Brush	Roller
Output Fluid Pressure	4000 psi	Yes	Yes
Tip size	19 thou		
Fan angle	50°		

Spraying Airless spray - the use of a heater block set at 35-40°C and a heavy duty pump such as a Graco King 63:1 is recommended. Plural component feed systems such as Hydracat may also be used. Further details available on request.

Brushing/Rolling Apply unthinned. When brushing, lay on, do not over brush. When rolling, a short nap lambs wool roller is recommended.

Mixing Mix each component separately prior to thoroughly mixing together for 2 to 3 minutes at medium speed. Over-mixing will create heat and reduce the working life. Always use a mechanical agitator. Ensure product is used only in the proportions recommended.

Stripe coating Stripe coat all edges, nuts, bolts, welds etc.

Overcoating Overcoatable with itself – for overcoating with other Corroless topcoats please consult Corroless. If overcoating time exceeds 24 hours and contamination has occurred, clean using a detergent solution/fresh water rinse and allow to dry before continuing. If maximum overcoating times are exceeded, abrade the surface and wash down with fresh water to remove contamination and allow to dry.

Application Temperature Range 8°C - 25°C.

Ambient Conditions Only apply in conditions of good ventilation, which should be maintained during drying. Do not apply when rain, mist, sleet or snow are imminent. During application and drying time the Relative Humidity should not exceed 85% and the steel temperature should remain at least 3°C above the dew point.

Flash Point Greater than 55°C.

Health and Safety At all times observe precautionary notices on containers. Refer to Material Safety Data Sheets available from Corroless on request.

This information is given in good faith for the guidance of users but without warranty or liability. Any queries should be referred to our Technical Department. The above information is based on laboratory tests and practical experience and has been proved valid at the date marked on the product data sheet. When necessary verify the validity of the product data sheet. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001. As a manufacturer we cannot be responsible for any damages caused by using the product against instructions or for inappropriate purposes. FOR PROFESSIONAL USE ONLY.