



Paints Limited

www.kenyonpaints.co.uk

FOR SALES & TECHNICAL SUPPORT

Call **0161 665 4470** Fax **0161 627 5072**

Email sales@kenyonpaints.co.uk

Kenyon Paints Limited Regent Street Oldham OL1 3TZ

Product Name:	MARGARD WATER WASHABLE GRAFFITI SYSTEM
Reference Number:	4-line
Coating Type:	Unique single pack moisture curing polymer.
Typical Uses:	Permanent anti-graffiti coating with excellent water washable graffiti removal properties for concrete, brick, coated metal etc(See note 1). Graffiti can be simply removed by pressure washing with water to produce the original coating without the use of solvents or gels.
Colours Available:	Clear
Appearance of Dried Film:	Gloss 4-2 Matt 4-3
Typical Coverage Gloss:	6-8 m ² /lt per coat may vary depending on porosity and nature of substrate.
Typical Coverage Matt:	4-6 m ² /lt per coat may vary depending on porosity and nature of substrate.
Drying Time at 20°C: (Will vary with temperature, air movement etc.)	Touch Dry: 1 hour Firm Dry: 2 hours Overcoat: 4 hours minimum
Packaging:	5 & 20 litre containers.
Shelf Life:	6 months in unopened containers, when stored under cover in good storage conditions.
Storage:	Under cover within temperature range of 5°C to 32°C.
Surface Preparation:	Ensure substrate is sound, clean, dry and free from any form of contamination / graffiti. If necessary prime/seal the substrate with the appropriate sealer e.g. Margard Non Darkening Sealer ref: 4-1.

continued

Application: Apply two full coats by brush/roller (See note 2). Do not overbrush or roll to ensure optimum film build and finish. Once dried the coating will exhibit a characteristic 'rubbery' feel which indicates a suitable film build for easy graffiti removal.

Cleaning Graffiti: **Small areas:** can be cleaned off using preferably warm water and a scrubbing brush.

Large areas: pressure washing preferably with warm water (50°C approx) with a maximum working pressure of 1000 psi.

Clean Up: Immediately with Dacrylate Thinner R1.

Note 1: Once applied this material is a permanent coating and cannot be over painted at any point other than with itself as and when required to 'refresh' the coating.

Note 2: Very porous substrates may require a further application of Margard Water Washable Graffiti System.

Certain substrates may darken slightly with the coating. Margard Non Darkening Sealer ref: 4-1 can be applied to the substrate where the original substrate appearance needs to be retained. A trial area is always advisable to determine acceptable appearance.

For application to previously painted substrates coated with graffiti or other types of painted/unpainted substrates, please contact Dacrylate Technical Department for further advice.

Health and Safety: Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.

Issued: July 2005

KW/DAE/HC