



Paints Limited

www.kenyonpaints.co.uk

FOR SALES & TECHNICAL SUPPORT

Call **0161 665 4470** Fax **0161 627 5072**

Email sales@kenyonpaints.co.uk

Kenyon Paints Limited Regent Street Oldham OL1 3TZ

| | |
|---|---|
| Product Name: | DACRYLATE METAL PRIMER |
| Reference Number: | 40-Line |
| Coating Type: | Long Oil Alkyd with iron-oxide pigments. |
| Typical Uses: | Low cost primer for protection of steelwork, with good adhesion and durability. |
| Colours Available: | Grey ref: 40-6 Red Oxide ref: 40-1 |
| Appearance of Dried Film: | Low sheen |
| Volume Solids: | 50% |
| Dry Film Thickness: | Typical: 40 microns |
| Theoretical Coverage: | 12.5m ² per litre at 40 microns dry film thickness |
| Drying Time at 20°C: (Will vary with temperature, air movement etc.) | Touch Dry: 2 Hours Firm Dry: 4 Hours Overcoat: overnight |
| Packaging: | 5 litre containers |
| Shelf Life: | 2 years in unopened containers, when stored under cover in good storage conditions. |
| Storage: | Under cover within temperature range of 5°C to 32°C. |
| Surface Preparation: | Preferred method is abrasive blast to ISO 8501-1. Sa2.5 Manual Clean – chip, scrape and power wire brush to remove all loose millscale, rust, etc. Any previous coatings remaining must be sound with good adhesion. Feather all edges to achieve smooth profile. Degrease immediately prior to painting using Dacrylate Thinner R1 or R70. |

Continued

- Application:** Conventional Spray
May require addition of up to 10% Dacrylate thinner R70 to achieve optimum spray characteristics
- Brush
Ready for use
- Apply **unthinned** material at an approximate wet film thickness of 80 microns to achieve a dry film thickness of 40 microns.
- Overcoating:** May be over coated with any white spirit based finishes, e.g. Vehicle and Machinery Enamel ref: 97-line, QD2 Enamel ref: 6-line, Alkysil Gloss ref: 1-line, Dacsil ref: 17-line.
- Clean Up:** Dacrylate Thinner R1 or R70.
- Health and Safety:** Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.

Issued: September 2001 SW/DAE/WHC