



Paints Limited

www.kenyonpaints.co.uk

FOR SALES & TECHNICAL SUPPORT

Call **0161 665 4470** Fax **0161 627 5072**

Email sales@kenyonpaints.co.uk

Kenyon Paints Limited Regent Street Oldham OL1 3TZ

Product Name:	GLODAC BASECOAT
Reference Number:	95-56
Coating Type:	Modified urethane.
Typical Uses:	As a white basecoat to give fluorescent colour when overcoated with Glodac fluorescent paints.
Colours Available:	White.
Appearance of Dried Film:	Matt.
Volume Solids:	47%.
Dry Film Thickness:	Typical: 50 microns.
Theoretical Coverage:	9.4m ² per litre at 50 microns.
Drying Time at 20°C: (Will vary with temperature, air movement etc.)	Touch Dry: 2 hours. Firm Dry: 4 hours. Overcoat: Overnight.
Packaging:	1 litre and 2.5 litre containers.
Shelf Life:	2 years in unopened containers, when stored under cover in good storage conditions.
Storage:	Under cover within temperature range of 5°C to 32°C.
Surface Preparation:	<u>Steel</u> Thoroughly wire brush to remove all rust etc., to leave a sound surface. Degrease with Dacrylate Thinner R1. <u>Wood</u> Ensure surface is clean and dry. <u>Previously Painted Surfaces</u> Lightly abrade then degrease with Dacrylate Thinner R1.
Application:	<u>Brush</u> - Apply evenly by brush. <u>Conventional Spray</u> - Adjust to spray consistency with Dacrylate Thinner R70.
Clean Up:	Dacrylate Thinner R1.
Health and Safety:	Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.

Issued: November 2001 SW/DAE/CR