

Truguard Flexible Exterior Gloss

Leyland Truguard Flexible Exterior Gloss outperforms conventional gloss systems by up to two years. Formulated on flexible alkyd resins, this product provides an exceptionally durable and water-resisting gloss finish for exterior timber, metal and PVCu surfaces.



The British Board of Agrément is designated by Government to issue European Technical Approvals based on the assessment of products for construction. Leyland's products carrying this logo have undergone rigorous independent testing and received approval from the BBA.

Recommended uses

Interior **X** Exterior **✓**

Type of substrate

Softwood, hardwood and plywood panels.
Also suitable for use on metal.

Colour availability

Brilliant White & Black (2.5ltr & 750ml)

Finish

Gloss

Volume solid

61%

Coverage

1 litre will cover approximately 15 square metres, depending on the nature and porosity of the surface.

Drying time

Touch dry in 4-6 hours.
Recoat after 16-24 hours.

Transportation and storage

To avoid the risk of spillage, always store and transport in a secure upright position.
Store away from heat and flame.

VOC content

HIGH VOC CONTENT 25-50%
VOCs (Volatile Organic Compounds) contribute to atmospheric pollution.

EU limit value for this product (Cat A/d): 300 g/l (2010). This product contains max 300 g/l VOC.

Film thickness

Wet: 67µm
Dry: 41µm

Preparation

Ensure surface to be painted is sound, clean, dry and free from grease. Remove all loose and defective paint. Rub down sound glossy surfaces with fine waterproof abrasive paper to provide a key. Avoid the inhalation of dust. Wear a suitable face mask if dry sanding. Treat any mould or lichen with sterilisation wash as directed. For maximum performance, old paint or varnish should be completely removed. Treat new or bare timber surfaces with clear preservative, prime metal surfaces

with an appropriate primer. Follow with a coat of Leyland Truguard Flexible Exterior Undercoat then two coats of Leyland Truguard Flexible Exterior Gloss. Special precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain harmful lead. For further advice contact Technical Advisory.

Application

Stir well before use. Apply paint evenly by brush or roller and avoid overspreading. The brush should be fully loaded for best results.

Cleaning

Remove as much product as possible from application equipment before cleaning. Clean equipment immediately after use with white spirit or turpentine substitute. Some local authorities have special facilities for disposal of waste coatings. Do not empty product into drains or watercourses. Replace lid firmly.

Warning

- Flammable liquid and vapour.
- May cause an allergic skin reaction.
- Hazardous ingredients: 4,5-dichloro-2-octyl-3(2H)-isothiazolin-3-one.
- Contains 2-butanone oxime. May produce an allergic reaction.
- Safety data sheet available on request.
- Repeated exposure may cause skin dryness or cracking.
- Keep away from heat, hot surfaces, sparks, open flames, and other ignition sources. No smoking.
- If medical advice is needed, have product container or label at hand.
- Keep out of reach of children.
- Dispose of contents/container to a waste disposal site in accordance with local/national regulations.
- Do not get in eyes, on skin, or on clothing.
- Wear protective gloves/protective clothing/eye/face protection.
- IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.
- IF ON SKIN: Wash with plenty of water. Do not use solvent thinners or White Spirit.
- IF SWALLOWED: Call a POISON CENTRE or doctor if you feel unwell.
- Ensure maximum ventilation during application and drying.
- Store in a well-ventilated place. Keep cool.
- Keep container tightly closed.

